

## Steel 22 & 24 Gauge (AZ50 Galvalume) | Color Offerings

				
<b>Deep Black</b> SR .27 SRI 25	<b>Matte Black</b> SR .27 SRI 25	<b>Charcoal Gray</b> SR .25 SRI 23	<b>Musket Gray</b> SR .35 SRI 35	<b>Slate Gray</b> SR .38 SRI 38
				
<b>Ash Gray</b> SR .50 SRI 56	<b>Almond</b> SR .61 SRI 72	<b>Bright White</b> SR .68 SRI 81	<b>Bone White</b> SR .68 SRI 81	<b>Stone White</b> SR .66 SRI 77
				
<b>Cityscape</b> SR .45 SRI 51	<b>Extra DK Bronze</b> SR N/A SRI N/A	<b>Sandstone</b> SR .60 SRI 69	<b>Sierra Tan</b> SR .46 SRI 50	<b>Medium Bronze</b> SR .31 SRI 31
				
<b>Mansard Brown</b> SR .26 SRI 25	<b>Burnished Slate</b> SR .25 SRI 33	<b>Dark Bronze</b> SR .28 SRI 27	<b>Hartford Green</b> SR .27 SRI 25	<b>Classic Green</b> SR .31 SRI 30
				
<b>Hemlock Green</b> SR .31 SRI 31	<b>Teal</b> SR .28 SRI 27	<b>Slate Blue</b> SR .33 SRI 33	<b>Royal Blue</b> SR .27 SRI 26	<b>Regal Red</b> SR .39 SRI 41
				
<b>Colonial Red</b> SR .33 SRI 35	<b>Burgundy</b> SR .27 SRI 26	<b>Terra Cotta</b> SR .42 SRI 45	<b>Aged Copper *</b> SR .27 SRI 26	<b>Vintage *</b> SR .30 SRI 22
				
<b>Western Rust *</b> SR .24 SRI 23	<b>Copper Penny *</b> SR .44 SRI 48	<b>Weathered Zinc *</b> SR .38 SRI 41	<b>Silver *</b> SR .56 SRI 63	<b>Champagne *</b> SR .47 SRI 51
				
<b>Acrylic Coated Galvalume</b> SR N/A SRI N/A				

**\* Premium Color**

A 35-year PVDF warranty covers performance criteria including color-fastness, fade, chalk, and film integrity.

Colors shown represent the actual colors as accurately as modern printing technology will permit.

**Solar Reflectivity (SR):** Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance.

**Solar Reflectance Index (SRI):** The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing.

Oil canning is an inherent part of light gauge cold-formed metal products and is not cause for coil, sheet or panel rejection.

Protective film must be removed during installation.

Coated with **Dura Coat Durapon** 70% full strength PVDF paint finishes formulated with Cool technology.

Additional standard and custom colors are available with minimum order requirements